

Appl. No. 10/506,487  
Amdt. Dated September 26, 2006  
Reply to Office Action of June 26, 2006


**Amendment to the Claims:**

This listing will replace all prior versions, and listings, of the claims in the application:

**Listing of Claims:**

Claim 1 (Currently amended): A metal- or resin-laminated gasket, which comprises a cured product layer of a composition comprising:

(A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction obtained by copolymerization of an acrylic acid ester monomer and a compound as a second monomer represented by the general formula:



wherein  $\text{R}^1$  is a hydrogen atom or a methyl group and  $\text{R}^4$  is an alkyl ~~organic~~ group of  $\text{C}_1\text{-C}_{20}$ , which may have at least one ether bond;

(B) a hydrosilyl group-containing compound; and

(C) a hydrosilylation catalyst as essential components, and a metal plate or resin plate, the cured product layer being provided on at least one surface of the metal plate or the resin plate.

Claim 2 (Previously presented): A metal- or resin-laminated gasket according to claim 1, wherein the component (A) of the composition is a liquid acrylic polymer having a number

Appl. No. 10/506,487  
Amdt. Dated September 26, 2006  
Reply to Office Action of June 26, 2006

average molecular weight  $M_n$  of 500 or more and a molecular weight distribution ( $M_w/M_n$ ) of 1.8 or less.

Claim 3 (Previously presented): A metal- or resin-laminated gasket according to claim 1, wherein the cured product layer has a film thickness of 1-500  $\mu\text{m}$ .

Claim 4 (Previously presented): A metal- or resin-laminated according to claim 1, wherein the cured product layer has a surface hardness (Duro hardness A) of 45 or less.

Claim 5 (Previously presented): A metal- or resin-laminated gasket according to claim 1, wherein the composition is directly applied to an adhesive-coated metal plate or resin plate and cured.

Claim 6 (Previously presented): A metal- or resin-laminated gasket according to claim 1, which comprises at least one of an automobile engine cylinder head gasket, an engine oil pan gasket and an engine intake-exhaust manifold gasket.

Claim 7 (Previously presented): A metal- or resin-laminated gasket according to claim 1, wherein the cured product is provided on a resin plate that has a softening point of 100°C or more.

Appl. No. 10/506,487  
Amdt. Dated September 26, 2006  
Reply to Office Action of June 26, 2006

Claim 8 (Previously presented): A metal- or resin-laminated gasket according to claim 2, which comprises at least one of an automobile engine cylinder head gasket, an engine oil pan gasket and an engine intake-exhaust manifold gasket.

Claim 9 (Previously presented): A metal- or resin-laminated gasket according to claim 3, which comprises at least one of an automobile engine cylinder head gasket, an engine oil pan gasket and an engine intake-exhaust manifold gasket.

Claim 10 (Previously presented): A metal- or resin-laminated gasket according to claim 4, which comprises at least one of an automobile engine cylinder head gasket, an engine oil pan gasket and an engine intake-exhaust manifold gasket.

Claim 11 (Previously presented): A metal- or resin-laminated gasket according to claim 2, wherein the cured product is provided on a resin plate that has a softening point of 100°C or more.

Claim 12 (Previously presented): A metal- or resin-laminated gasket according to claim 3, wherein the cured product is provided on a resin plate that has a softening point of 100°C or more.

Appl. No. 10/506,487  
Amdt. Dated September 26, 2006  
Reply to Office Action of June 26, 2006

Claim 13 (Previously presented): A metal- or resin-laminated gasket according to claim 4, wherein the cured product is provided on a resin plate that has a softening point of 100°C or more.

Claim 14 (Previously presented): A metal- or resin-laminated gasket according to claim 1, wherein the second monomer is one of 1,5-hexadiene, 1,7-octadiene and 1,9-decadiene.

Claim 15 (Currently amended): A metal- or resin-laminated gasket according to claim 1, wherein the second monomer reacts at a final stage of the polymerization ~~react~~ reaction or after completion of the reaction of the acrylic acid ester monomer in the synthesis of acrylic polymers by living radical polymerization.